



EASTERN POLY CO., LTD

Look to us for all your domestic or import Woven Geo-Textiles

Trang Bang Industrial Park, Trang Bang District, Tay Ninh Province

Viet Nam

Our woven polypropylene Geo Series manufactured and tested in our Viet Nam facility meets all criteria to be N.T.P.E.P. compliant.

GTX-2016-01-192

EP-200

Minimum Average Roll Values when tested in accordance with the ASTM methods listed below.

Property	Test Method	Imperial	Metric
Mass per Area		3.7 oz.sq.yd	128 gsm
Grab Tensile Strength warp	ASTM D-4632	253 lbs	1125 N
Grab Tensile Strength weft	ASTM D-4632	235 lbs	1045 N
Elongation	ASTM D-4632	16 %	16 %
CBR Static Puncture	ASTM D-6241	699 lbs	3109 N
Trapezoidal Tear warp	ASTM D-4533	102 lbs	454 N
Trapezoidal Tear weft	ASTM D-4533	100 lbs	445 N
UV Resistance (retained after 500 hrs)	ASTM D-4355	75 %	75 %
Apparent Opening Size	ASTM D-4751	60 sieve	.25 mm
Permittivity	ASTM D-4491	0.05 sec-1	0.05 sec-1
Flow Rate	ASTM D-4491	4 gpm/ft2	163 lpm/m2

Seller makes no warranty, expressed or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specification stated herein.

Canadian Office:

Eastern Poly Canada Inc. 292116 Cross Pointe Drive, Rocky View County, Alberta, T4A-0V2

Patrick Kennedy Tel: 403-389-4744 email: patrick@easternpolycanada.com

