

WOVEN GEO-TEXTILES

HP 370



EASTERN POLY CO., LTD

Minimum Average Roll Values when tested in accordance with the ASTM methods listed below.

Property	Test Method	Imperial	Metric
Mass per Area	ASTM D-5261	7.1 oz/sq/yd	240gsm
Grab Tensile Strength	ASTM D-4632	496lbs/456lbs	2204 N/2026N
Elongation	ASTM D-4632	18-24%	18-24%
Static Puncture	ASTM D-6241	1400lbs	6222N
Trapezoidal Tear	ASTM D-4533	165lbs	733N
UV Resistance(retained after 1200hrs)	ASTM D-4355	70%	70%
Apparent Opening Size	ASTM D-4751	50-70 US Sieve	0.2-0.3 mm
Permittivity	ASTM D-4491	0.5 sec-1	0.5 sec-1
Flow Rate	ASTM D-4491	34.3gal/min/ft2	1400/min/m2

Seller makes no warranty, expressed or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specification stated herein.